HDI Waterborne Covesro XP2547

ABOUT:

Hydrophilic aliphatic polyisocyanate based on hexamethylene diisocy anate (HDI). Hardener for waterborne two-component polyurethane coatings.

Product Types:

No data available

Material:

No data available

General Characterization:

Hydrophilic aliphatic polyisocyanate based on hexamethylene diisocy anate (HDI).

Hardener for waterborne two-component polyurethane coatings.

Logistics and Handling

Storage Conditions:

- Storage in original sealed Covestro container.
- Recommended storage temperature: 0 30 °C.

- Protect from moisture, heat and foreign material.

General information: Hydrophilic isocyanates are very moisture-sensi tive and react with water to form carbon dioxide and insoluble ur eas. The containers must always be kept tightly closed. The access of water in all forms (moist air, solvents, moist containers) must b e prevented, because the generation of carbon dioxide can lead to dangerous increases in pressure. Storage at higher temperatures wi II result in increase of color and viscosity.

Sampling:

No data available

Technical Properties & Datasheets

Characteristics:

Property Name	Test Method	Unit	Value
Density at 20	DIN EN ISO 2811	g/ml	approx. 1.15
°C			
Flash point	DIN EN 22 719	°C	approx. 185

Specifications:

Property Name	Test Method	Unit	Value
Hazen color value	M017-EN 1557		≤ 150

Monomeric HDI	M016-ISO 10283	%	< 0.26
NCO content	M105-ISO 11909	%	22.5 ± 0.5
Viscosity at 23 °C	M014-ISO 3219/	mPa*s	570 - 730
	A.3		

Packaging:

200KG/drum Please fasten the packaging cover as soon as possible after original packaging to prevent the mixing of other substances such as moisture and other substances that may affect the performance of the product. Do not inhale dust, avoid skin and mucous membrane contact. Smoking, eating and drinking are prohibited in the workplace. After work, shower and change clothes. Store contaminated clothes separately and reuse them after washing. Maintain good hygiene practices.

E_mail us : info@allhdi.com