

## HDI trimer WanHua HT-90BS

### Application:

[WANNATE®HT-90BS](#) is an aliphatic polyisocyanate based on hexamethylene diisocyanate(HDI) and dissolved in 10% n-butyl acetate and solvent naphtha 100(1:1),colorless to slightly yellowish clear liquid.

Equivalent weight	approx. 214
Density at 25°C	approx. 1.13g/ml
Flash point	approx. 50°C

WANNATE® HT-90BS can be used as the hardener component for lightfast two-component polyurethane coatings with high resistance to chemicals and weathering, very good gloss retention and outstanding mechanical properties.

Preferred co-reactants are polyacrylates or polyester polyols.

The main applications for coatings based on WANNATE® HT-90BS are automotive OEM, automotive refinishing, transportation, industrial finishing and plastics.

### Specification:

Properties	Specification
NCO Content	19.6 ± 0.3 %

Solids	90 ± 1 %
Viscosity at 25°C	500 ± 150 mPa•s
Color value (Hazen)	≤ 40
Monomeric HDI	≤ 0.2 %

**Package(s):**

20 Kg      Metal drum

220 Kg     Metal drum

**Storage/ Solubility:**

Storage in original container. Protect from moisture, heat and foreign material.

WANNATE® HT-90BS is sensitive to moisture. Storage at higher temperatures will result in increase of color and viscosity.

WANNATE® HT-90BS can be thinned with esters, ketones and aromatic hydrocarbons such as ethyl acetate, butyl acetate, methoxypropylacetate, acetone, methyl ethyl ketone, methyl isobutyl ketone, cyclohexanone, toluene, xylene, solvent naphtha 100 and mixtures thereof. Generally speaking, it has good compatibility with the solven

ts listed. However, the solutions formed must be tested for their storage stability. Only PU grade solvents should be used (max.0.05% water, absence of reactive groups such as hydroxyl or amino groups). Aliphatic hydrocarbons are unsuitable as solvents.

WANNATE® HT-90BS is not recommended to thin to a lower solid content. Prolonged storage of a solution with a lower content may result in turbidity and sedimentation, even condensation.

**Compatibility:**

WANNATE® HT-90BS can be mixed with the following products: aliphatic polyisocyanates, polyester polyols, aromatic polyisocyanates and polyacrylates.

**Shelf Life:**

It can be stored at least for 9 months at room temperature if stored properly.

**Safety Hazards identification:**

May cause sensitization by skin contact. Contains isocyanates. See information supplied by the manufacturer.

The product is used mainly as a hardener in coating materials or

adhesives. The handling of coating materials or adhesives containing reactive polyisocyanates and residual monomeric HDI requires appropriate protective measures referred to in the safety data sheet. These products may therefore be used only in industrial or trade applications. They are not suitable for use in homemaker (DIY) applications.

The safety data sheet should be observed. This contains information on labeling, transport and storage as well as on handling, product safety and ecology.

**E\_mail us :** [info@allhdi.com](mailto:info@allhdi.com)